

Technical Data Sheet

DOWSIL™ 3793 Insulating Glass Sealant

One-part silicone rubber

Features & Benefits

- Outstanding resistance to UV and moisture
- Good adhesion to a range of glasses (coated and reflective), metals and plastics, including acrylics polyamides, polycarbonate and uPVC
- Neutral curing sealant odorless, non-corrosive
- Good mechanical properties: high tear strength, elongation and tensile strength
- Cured material flexible from 40°C (-40°F) to 150°C (302°F)
- Solvent free
- Cure rate 2 mm depth in 24 hours measured at ambient temperature
- Thixotropic, non-slump, can be dispensed over a wide range of winter and summer conditions
- No mixing or catalyzing, only simple dispensing required
- Short tack free time 50 minutes (measured at ambient temperature)
- Resistant to ozone and temperature extremes

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
	Slump or flow	mm	0
ASTM D0412	Tensile strength	MPa	2.85
ASTM D0412	Elongation at break	%	600
ASTM D624	Tear strength	kN/m	19
ASTM D2240	Durometer hardness, Shore A	points	38
	Specific gravity		1.43
	Tack free time	minutes	50
	Extrusion rate (3.2 mm nozzle at 6.3 kg/cm²)	g/minute	170

ASTM: American Society for Testing and Materials.
 The data presented have been obtained with unpigmented product.
 N.B. Final mechanical properties measured after 7 days curing at 25°C (77°F) and 50% R.H.

Description

DOWSIL™ 3793 Insulating Glass Sealant is a high performance, moisture curing, one-part neutral sealant, specifically designed for the insulating glazing industry for the production of hermetically sealed units. DOWSIL™ 3793 Insulating Glass Sealant exhibits excellent unprimed adhesion to the commonly used materials in the industry including glass, aluminum, galvanized steel, certain plastics and reflective glasses.

Priming

This product features adhesion to a variety of non-porous substrates; however, for specific substrates, priming could be necessary to improve adhesion. Please consult our Primer Selection Guide, or consult our technical service department.

Cure

Neutral alkoxy cures at room temperature on exposure to atmospheric moisture in the air, giving off a small amount of methanol.

Surface Preparation

As with any sealant, all surfaces must be clean and dry. Degrease or remove any contaminants which could impair adhesion using suitable solvents.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life and Storage

When stored at or below 30°C (86°F) in the original unopened containers, this product has a usable life of 12 months from the date of production.

Packaging Information

This product is available in 180 liter drums.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

Form No. 62-1007-01-0623 S2D

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

